

08/10/31

Certificate of Specification

Grade : DENKA Chloroprene M-40

			TEST Method
Appearance	:	Chips, free from foreign materials except for talc	DTD-1
Color	:	White to amber	DTD-1
Mooney Viscosity	:	43~53 ML ₁₊₄ (100°C)	DTD-2
Volatile Matter	:	≦ 1.0 wt%	DTD-3
Scorch Time (t ₅)	:	15 ± 4 min	DTD-6,7
500% Modulus	:	1.0 to 4.0 MPa	DTD-6,9
Tensile Strength	:	≧ 15.0 MPa	DTD-6,9
Elongation	:	≧ 750%	DTD-6,9