

08/11/05

Certificate of Specification

Grade : DENKA Chloroprene PS-40A (H)

		TEST Method
Appearance	: Chips, free from foreign materials except for talc	DTD-1
Color	: Amber	DTD-1
Mooney Viscosity	: 45~55* ML ₁₊₄ (100°C)	DTD-2
Volatile Matter	: ≤ 1.0 wt%	DTD-3
500% Modulus	: 2.0 to 5.0 MPa	DTD-6,9
Tensile Strength	: ≥ 23.0 MPa	DTD-6,9
Elongation	: $\geq 800\%$	DTD-6,9

* at Production