



versalis

[www.versalis.eni.com](http://www.versalis.eni.com)

## Technical Data Sheet

[info.elastomers@versalis.eni.com](mailto:info.elastomers@versalis.eni.com)

### DUTRAL<sup>®</sup>

EP(D)M

### CO 059

Ethylene - Propylene Copolymer

Dutral<sup>®</sup> CO 059 is an Ethylene - Propylene polymer produced by suspension polymerisation using a Ziegler-Natta Catalyst at the Ferrara production facility in Italy.  
A non-staining antioxidant is added during the production process.

#### Main Properties

#### Unit

#### Typical Value

Mooney Viscosity ML 1+4(125 °C)	MU	79
Volatiles content	% wt	0.5 max
Ash content	% wt	0.3 max
Propylene content	% wt	41

#### Key Features

Dutral<sup>®</sup> elastomers are characterized by excellent resistance to ageing and weathering, good resistance to both high and low temperatures, low permanent set values, good resistance to a large number of chemicals.

Dutral<sup>®</sup> CO 059 is an amorphous, high molecular weight copolymer.

It can accept high level of filler maintaining good low temperature properties.

#### Main Applications

Polymer modification, mechanical goods, building.

#### Physical Form

Bales wrapped with natural polyethylene film; typical bale weight: 25 kg.

#### Packaging

Cardboard box of 750 kg containing 30 bales (1050 x 1250 x h1050 mm).

#### Storage Conditions

Store in vented, dry area at temperatures between 20°C and 30°C; no direct sunlight.

Shelf life : 36 months.

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee, expressed or implied, is made nor liability accepted with respect to the use of such information and data.