

www. versalis.eni.com

## **Technical Data Sheet**

info.elastomers@versalis.eni.com

# **EUROPRENE®**

N 3345

BR Acrylonitrile-Butadiene Rubbers

Europrene® N 3345 is a cold polymerized acrylonitrile-butadiene copolymer made at the Porto Torres production facility in Italy. A non staining antioxidant is added during the production process.

Main Properties	Test Method	Typical Value	
ACN Content, % wt	ASTM D 3533	33	
Mooney Viscosity ML 1+4(100 °C)	ASTM D 1646	45	
Volatile matter, % wt	ASTM D 5668	0.7 max	
Ash, % wt	ASTM D 5667	0.5 max	
Organic Acid, % wt	ASTM D 5774	0.5 max	
Soap, % wt	ASTM D 5774	0.6 max	

#### **Key Features**

Europrene® N 3345 is characterised by good processability, good mineral oil resistance, and medium flexibility at low temperature. The vulcanization can be performed by sulphur based systems or by peroxides. The low temperature properties can be improved by adding polar plasticizers as synthetic esters of adipic, sebacic or phtalic acids. To improve heat, light and ozone resistance, suitable protective agents as amine or phenolic antioxidants have to be added in the compounding process.

## **Main Applications**

Wide range of oil resistance technical articles: seals, industrial shoes soles, seals, technical goods, etc.

#### **Physical Form**

Light yellow bales wrapped in a strippable and easily dispersible polyethylene film (softening Vicat point: 90-100 °C)

### **Packaging**

Wooden crate IPPC, 30 kg bale, 40 bales per crate (1090 x 1250 x H1450 mm).

Wooden crate IPPC for over seas market, 30 kg bale, 30 bales per crate (1090 x 1250 x H1100 mm).

Label on the crate indicating the type, lot number, crate number, nominal net weight.

Polyethylene strip on bales with product type printed on it.

## **Storage Conditions**

Shelf life 24 months.

Store in vented , dry area at tempertures between 20°C and 30°C, no direct sunlight.

Please consult the relevant safety data sheet for more detailed information.

The information and data presented herein are to the best of our knowledge true and accurate, but no warranty or guarantee, is made nor liability accepted with respect to the use of such information and data.

® Registered Trademark
1204