

Tecnoflon® FOR 9383

fluoroelastomer

TECNOFLON® FOR 9383 is a medium-high viscosity cure incorporated fluoroelastomer terpolymer (FKM) with 68.5% fluorine content. Tecnoflon® FOR 9383 is well suited for all applications requiring better chemical resistance and/or long term heat resistance compared to fluoroelastomer copolymers and in any application requiring adhesion to metal. Tecnoflon® FOR 9383 contains proprietary cure system providing superior processability for fast cycles and scorch safety.

Some of the basic properties of TECNOFLON® FOR 9383 are:

- Very good processability
- Excellent chemical resistance
- Good hot tear resistance
- Good heat resistance

- · Good bonding to metal
- Very good scorch safety

Tecnoflon® FOR 9383 can be used for compression, injection and transfer moulding of shaft seals, valve stem seals, gaskets or any item requiring excellent chemical resistance.

This material can be combined with the cure system and other typical fluoroelastomer compounding ingredients. Mixing can be accomplished with two-roll mills or internal mixers.

Tecnoflon® FOR 9383 can be extruded into hoses or profiles and can be calendered to make sheet stocks or belting. Finished goods can be produced by a variety of rubber processing methods.

General

Material Status	 Commercial: Active 		
Availability	• Europe	North America	
Additive	Processing Aid		
Features	BondabilityFast Molding CycleGood AdhesionGood Chemical Resistance	 Good Heat Aging Resistance Good Processability Good Tear Strength High Heat Resistance 	Medium-high ViscosityTerpolymer
Uses	Belts/Belt RepairBlendingGaskets	 Hose Profiles Seals	SheetValves/Valve Parts
Appearance	Off-White		
Forms	• Slab		
Processing Method	CalenderingCompounding	Compression MoldingExtrusion	Injection MoldingResin Transfer Molding

Physical	Typical Value Unit	Test method
Mooney Viscosity 1 (ML 1+10, 121°C)	60 MU	No Standard
Fluorine Content ¹	69 %	No Standard

Tecnoflon® FOR 9383

fluoroelastomer

Notes

Typical properties: these are not to be construed as specifications.

¹ Raw polymer

www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa SpecialtyPolymers.Americas@solvay.com | Americas SpecialtyPolymers.Asia@solvay.com | Asia and Australia



Material Safety Data Sheets (MSDS) are available by emailing us or contacting your sales representative. Always consult the appropriate MSDS before using any of our products. Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.