

Tecnoflon® T 636/L

fluoroelastomer

TECNOFLON® T 636/L is a low viscosity fluoroelastomer terpolymer designed to provide improved low temperature characteristics. Tecnoflon® T 636/L does not contain curatives: therefore the proper levels of Tecnoflon® FOR M1 and Tecnoflon® FOR M2 must be added to achieve the required properties. Tecnoflon® T 636/L is a lower viscosity version of Tecnoflon® T 636: please refer to Tecnoflon® T 636 Technical data sheet for data on chemical resistance: Tecnoflon® T 636/L exhibits the same excellent heat and chemical resistance expected from Tecnoflon® copolymers.

Some of the basic properties of TECNOFLON® T 636/L are:

- Improved low temperature performance
- Good heat and chemical resistance
- Very low compression set

- Excellent mould release
- · Lack of mould fouling
- Superior mould flow

Tecnoflon® T 636/L can be used for compression, injection and transfer molding of O-rings, diaphragms, gaskets, seals, moulded shapes or other items requiring improved low temperature performance. Tecnoflon® T 636/L can be combined with the cure system and other typical fluoroelastomer compounding ingredients. Mixing can be accomplished with two-roll mills or internal mixers. This material can be extruded into hoses or profiles and can be calendered to make sheet stocks or belting. Finished goods can be produced by a variety of rubber processing methods.

General

General			
Material Status	 Commercial: Active 		
Availability	• Europe	North America	
Features	Good Chemical ResistanceGood FlowGood Mold Release	High Heat ResistanceLow Compression SetLow Viscosity	• Terpolymer
Uses	Belts/Belt RepairBlendingDiaphrams	GasketsHoseLow Temperature Applications	 Profiles Seals Sheet
Appearance	Translucent		
Forms	• Slab		
Processing Method	CalenderingCompounding	Compression MoldingExtrusion	Injection MoldingResin Transfer Molding
Physical		Typical Value Unit	Test method
Mooney Viscosity 1 (ML 1+10, 121°C)		22 MU	No Standard
Fluorine Content ¹		66 %	No Standard

Tecnoflon® T 636/L

fluoroelastomer

Notes

Typical properties: these are not to be construed as specifications.

¹ Raw polymer

www.solvay.com

SpecialtyPolymers.EMEA@solvay.com | Europe, Middle East and Africa SpecialtyPolymers.Americas@solvay.com | Americas SpecialtyPolymers.Asia@solvay.com | Asia and Australia



Material Safety Data Sheets (MSDS) are available by emailing us or contacting your sales representative. Always consult the appropriate MSDS before using any of our products. Neither Solvay Specialty Polymers nor any of its affiliates makes any warranty, express or implied, including merchantability or fitness for use, or accepts any liability in connection with this product, related information or its use. Some applications of which Solvay's products may be proposed to be used are regulated or restricted by applicable laws and regulations or by national or international standards and in some cases by Solvay's recommendation, including applications of food/feed, water treatment, medical, pharmaceuticals, and personal care. Only products designated as part of the Solviva® family of biomaterials may be considered as candidates for use in implantable medical devices. The user alone must finally determine suitability of any information or products for any contemplated use in compliance with applicable law, the manner of use and whether any patents are infringed. The information and the products are for use by technically skilled persons at their own discretion and risk and does not relate to the use of this product in combination with any other substance or any other process. This is not a license under any patent or other proprietary right. All trademarks and registered trademarks are property of the companies that comprise the Solvay Group or their respective owners.